

**Amendment to the specification:**

Amend Table 1 (page 16 of the specification) as indicated:

Polyether-silicone	Viscosity $\frac{\text{mm}^2}{\text{s}}$ (25°)	Refractive Index (25°)	Volatiles <sup>*2</sup> (105°C x 3 Hr)	Free Polyether <sup>*3</sup>
A	4.9	1.4298	2.2%	5%
B	9.7	1.4441	3.0%	6%
C	7.2	1.4330	2.2%	4%
D	8.7	1.4420	0.2%	0%
E	8.2	1.4425	0.1%	0%
F <sup>*1</sup>	9.4	1.4298	8.9%	15%
G	6.3	1.4285	1.9%	5%
H	9.5	1.4305	2.2%	6%